

TECHNICAL DATA SHEET

GLAZED PORCELAIN TILES

Nordik Floor Tiles - Satin Matt

MS ISO 13006: 2014, GROUP Bla E \leq 0.5%

	Standard Requirements	Internal Requirement	Test Result
Nominal Size Work Size		40x80cm 398.5 x 800.0 x 10.2mm	(Satin Matt) 40x80cm 398.5 x 800.0 x 10.2mm
Dimension and Surface Quality			
Dimension: Length & Width (Average)			
The deviation, in percent, of the average size for each tile from the work size	\pm 0.6% (Surface . 410 cm ²)	\pm 0.5%	Average: 398.5 x 800.1mm
Thickness	\pm 5.0%	\pm 5.0%	Average: 10.32mm
Surface Quality	Minimum 95%	Minimum 95%	100%
Physical Properties			
Water Absorption	E \leq 0.5%	E \leq 0.5%	Average = 0.11% Ind. Max = 0.12%
Breaking Strength, in N	Not less than 1300 N	\geq 1300 N	Average 2274 N
Modulus of Rupture (Mpa)	Minimum 35 N/mm ²	\geq 35 N/mm ²	Average = 53 N/mm ² Ind. Min = 51 N/mm ²
Slip Resistance Wet Pendulum Test (Factory test)	Manufacturer to State Value	PTV = P3 (MATT) PTV = P4 (GRIT)	PTV = 23 - 28 P2
Abrasion Resistance (PEI)	Report Abrasion Class	Min Class 3	Class 3 Cycle Passed: 750
Crazing Resistance	Required	No crazing observed	No crazing observed
Chemical Properties			
Resistance to staining: a) glazed tiles	Minimum Class 3	Minimum Class 3	1) Green staining agent in light oil 2) Iodine, 13g/l solution in alcohol 3) Olive Oil Result: Class 5
Resistance to low concentrations of acids and alkalis: a) glazed tiles	Manufacturer to state Classification	Minimum GLB	1) Hydrochloric acid solution, 3% 2) Potassium hydroxide solution 30g/l 3) Citric acids solution 100g/l Result: No visible effect (GLA)
Resistance to household chemicals and swimming pool salt a) glazed tiles	Minimum GB	Minimum GB	GA

The above Johnson Tiles technical specifications are a general indication only.

Please contact your local Johnson Tiles representative or state office for more detailed information.