

Technical Data Sheet

Peak

Peak Wall & Floor Tiles

| Wet Pendulum | Matt P3 | Matt P3 |
|---|---|--|
| | Grit P4 | Grit P4 |
| | | |
| Specifications | | |
| Nominal Size | 300x600mm | 600x600mm |
| Work Size | 299.5x600x8.3mm | 600x600x9mm |
| Dimensions and Surface Quality | | |
| Dimensions: Length (L) & width (W) The deviation (%) of the average size for each tile from work size | -0.2mm~-0.1mm | ± 0.15% |
| Thickness | +0.2mm~+0.4mm | ± 5.0% |
| Straightness of Sides | ±0.3% (±0.8mm) | ±0.3% (±0.8mm) |
| Rectangularity | ±0.3% (±1.5mm) | ±0.3% (±1.5mm) |
| Surface Flatness: | | |
| a) Centre Curvature | ±0.3% (±1.8mm) | ±0.3% (±1.8mm) |
| b) Edge Curvature | -±0.3% (±1.8mm) | ±0.3% (±1.8mm) |
| | | |
| c) Warpage | ±0.3% (±1.8mm) | ±0.3% (±1.8mm) |
| Surface Quality | 100% no defect noticeable from the sight of | 100% no defect noticeable from the sight o |
| | | |
| Physical Properties | | |
| Water Absorption | 0.10%~0.15% | E ≤ 0.5% |
| Breaking Strength, in N | 2097 | ≥ 1500 N |
| Modulus of Rupture | 56 | ≥ 40 N/mm² |
| Crazing Test | No Craze | No Craze |
| 5 | | 010 |
| Abrasion Resistance | Class 3 | Class 3 |



| Chemical Proper | | | |
|------------------------|-----------------------------------|-------------------------|-------------------------|
| a) Household chemicals | | А | Α |
| b) Swimming Pool Salt | | Α | Α |
| c) Acid and Alkali | | No visible effect (GLA) | No visible effect (GLA) |
| Staining Resistance | Green staining agent in light oil | Class 5 | Class 5 |
| | lodine, 13g/L solution in alcohol | Class 5 | Class 5 |
| | Olive oil | Class 5 | Class 5 |

The above Johnson Tiles technical specifications are a general indication only. Please contact your local Johnson Tiles representative or state office for more detailed information.